

Product Data Sheet MMC

Fundermax

For you to create

General requirements:

Properties	Test Method	Tolerance	Value	Unit
Length		± 2,0	2800	mm
With		± 2,0	1850	mm
Thickness		± 0,5	10-28	mm
Bending	EN 14323	± 2,0	-	mm/m

Technical properties:

Properties	Test method	Unit
Surface appearance	EN 438-2 Kap. 4	According to EN 438-3 Kap. 6.2.5.2 Dirt, stains and similar surface defects: max. 1,0 mm ² /m ² Fibres, hair and scratches: max. 10 mm/m ²
Gloss Level	EN 13722:2004	Measuring angle 85°: 7-16 GE
Cross cut test	ISO 2409:2007	GT ≤ 2
Lightfastness	DIN EN 15187:2006 Light fastness level 6	Grey scale ≥ 3,5
Resistance to cracking	DIN EN 14323	Hairline cracks present (>Grad 3)
Chemical stress	DIN EN 12720	DIN 68861-1: 1C
Scratch resistance	EN 438-2:2016	DIN 68861-4: E4 ≥ 1 N
Abrasion resistance	EN 438-2:2016	EN 438-3:2016 level 2 ≥ 50 turns
Dry heat	DIN EN 12722	DIN 68861-7: 7C (100 °C, level 5)
Wet heat	DIN EN 12721	DIN 68861-8: 8C (55 °C, level 5)
Humid climate / humidity resistance	AMK-MB-005:07/2007	Optical: No visible surface changes (cracks, bubbles, delamination of the coating material, colour change*)
Temperature resistance	AMK-MB-001:07/2007	Optical: No visible surface changes (cracks, bubbles, delamination of the coating material, colour change*)

Application

MMC (matt micro coated boards) is primarily used for vertical decorative applications in the interior. This product is not recommended for horizontal applications with load requirements.

Disclaimer

As a result of the constant further development of our products or any changes in the relevant standards and legal requirements, no legal claim can be derived from the information in this product data sheet!

Note:

This document has been drawn up to the best of our knowledge and with special diligence. We accept no liability for any mistakes, errors in standards or printing errors. In addition, technical modifications can result from the continuous further development, as well as from changes in standards and documents originating from statutory bodies.